



Multifunctional Compaction Aid, Hydration Enhancer and Waterproofing Additive for Production of Earth Moist / Semi Dry Floor Screed Mixes

General

SS - FloorScreed AD is a specially designed high-performance compaction aid, hydration enhancer and waterproofing additive for earth moist / semi dry mixes mostly employed in production and casting of floor levelling screeds. This is also suitable for employment in roller compacted concrete. This increases density of mix and improves one day strength. The increase of dispersion of cement paste results in lubrication in the mix and leads to a quick drying and setting floor screed that can be overlaid quickly. This helps the screed not to stick to tools ensure a smooth level screed finish.

The success of semi dry mixes depends on its mix design as it contains very less binders and more granular materials. The main problem to address is how to increase formation of slurry, which would also contribute to better surface properties with respect to both efflorescence as well as pigment dispersions. **SS - FloorScreed AD** addresses these problems, while maintaining stability of cast product as well imparting higher strength to the mix to maintain its dimensional stability immediately upon casting.

SS - FloorScreed AD helps provide improved material flow and extrusion property. It is one of the most economical ways to level floors prior to tiling or floor coverings. It is quick drying and ready for overlay much faster compared to regular floor screeds.

Product Features

- Compaction aid for semi dry mixes
- Enables quick overlaying for the screed
- Chloride free and Lowers Efflorescence
- Maintains dimensional stability
- Increases initial strength
- Enhances surface finishes
- Lowers friction in mix
- Increases dispersion in mix
- Increases production and economy
- Aids in maintaining tools and planers
- Increases density of mix
- Improves impermeability and water tightness



Areas of Application

- Levelling screeds for residential applications
- Levelling screeds for industrial applications
- Underlays for tiles, carpets, other flooring systems
- Underlays for Resin Flooring Systems
- Roller Compacted Concretes
- Cement based landscaping products like edgings, kerbstones etc.
- Pavement slabs
- Hollow core slabs
- Lightweight Screeds [when used with cement, sand and lightweight aggregates]
- Insulation screeds [with EPS beads]



Areas of Application

Specification Keywords	Compaction Aid, Semi Dry Mixes, water reduction, medium workability, OPC, Blended Cements, Cement Products, fast drying, early strength, quick overlay, water impermeable.
Delivered As	Slightly Hazy Liquid
Storage Instructions	In Original Packing. In a cool dry place.
Shelf Life	12 Months from date of Manufacture.
Post Use	Use Complete Packs, Dispose packaging according to local regulations.
Packing Size	30 kg, 230 kg

Assess Build Chem Private Limited



Hazards and Safety



Technical Data

Sp. Gravity	1.00 +/- 0.05
Dosage	0.10 to 0.50% by weight of binder
pH	> 6
Chloride Content	< 0.1%
Ash Content	Negligible

Instructions for Use

Add **SS - FloorScreed AD** to the semi dry mix during mixing, along with the additional water. Do not add **SS - FloorScreed AD** to the dry aggregate/cement mix, as it reduces efficiency of the admixture. The admixture is most effective when dosed after about 70% of the mixing water has been added to concrete. The mixing time after addition of the admixture should be long enough to allow the admixture to plasticize the mix completely. The mix to be produced can be mixed in a standard mixers or a modern batching plant / pan mixer setup of processing machines. Normal cement sand ratios can vary from 1:3 to 1:6 depending on strength requirements.

In-case the admixture needs to be dosed on-site into transit mixers, please follow corresponding engineering and safety rules. Post addition, rotate the transit mixer drum at full speed for atleast 3 minutes, to allow the admixture to disperse homogenously. As with all chemical products, take care during use and storage to avoid contact with eyes, mouth, skin or food. In case of contact, rinse eyes and skin immediately with plenty of water.

If ingested, seek immediate medical attention. Keep away from children and animals. Reseal containers after use. Do not reuse containers for storing water or other consumable foods. Use Complete Packs.

Safety and Precautions

To determine individual technical suitability, test the admixture under application conditions. Please allow us to assist you for your concrete technology testing/needs. Follow relevant standards for production, placing and curing of concrete. As with any concrete, efficient curing is essential to develop final properties mechanical and durability properties.

Depending upon the concrete mix severe over dosage of the admixture may result in apparent incompatibility such as bleeding/segregation of concrete, quick loss of slump, excessive air entrainment, extended initial and final setting times etc. Slight overdosing would not severely affect the ultimate strength of concrete provided the concrete is properly mixed, handled and placed and adequately compacted and cured.